


PROCESS DETAILS

Process	Glass Passivated Mesa
Die Size	57 x 57 MILS
Die Thickness	8.6 MILS \pm 0.6 MILS
MT1 Bonding Pad Area	28 x 16 MILS
Gate Bonding Pad Area	10 x 9 MILS
Top Side Metalization	Al - 45,000Å
Back Side Metalization	Al/Mo/Ni/Ag - 32,000Å

GEOMETRY



BACKSIDE MT2

GROSS DIE PER 4 INCH WAFER

3,374

PRINCIPAL DEVICE TYPES

CQ92-2M
CQ223-2M
CQ89-2M

145 Adams Avenue
Hauppauge, NY 11788 USA
Tel: (631) 435-1110
Fax: (631) 435-1824
www.centalsemi.com

R0 (29 -March 2005)